

Better chemistry. Better business.

Hubbard-Hall Inc. • 563 South Leonard Street, Waterbury, CT 07608 • HubbardHall.com • 800-648-3412

Product Bulletin

Product Name: Metal Guard 850 Product Code: 2508050 Revision Date: May 19, 2020

Metal Guard® 850

Metal Guard 850 is a liquid rust preventative which when mixed with water, readily forms an effective rust preventative for iron and steel fabrications that are packaged and stored indoors. Metal Guard 850 was developed to replace rust preventatives based upon sodium nitrite and nitrite/amine systems.

Features & Benefits

| Does not contain sodium | Addresses environmental |
|---------------------------|-----------------------------|
| nitrite or amines | concerns |
| Excellent short-term rust | Prevents rust on high value |
| protection | parts between processes |
| Water soluble | Easily removed with a mild |
| | alkaline cleaner |
| Low foam | Excellent for use in spray |
| | washers |

Physical Data

| Specific gravity | 1.12 |
|-----------------------------|----------------------|
| Percentage of volatility by | Negligible |
| volume | |
| Vapor density (air =1) | Non-volatile |
| Evaporation rate (n-butyl | Non-volatile |
| acetate) | |
| Solubility in water | Soluble |
| Appearance and odor | Amber colored liquid |
| pH (conc) | 11.0 |

Typical Applications

- In-process short-term rust inhibitor
- Can be used as a pre-paint sealer at concentrations less than 1% by volume









Better chemistry. Better business.

Hubbard-Hall Inc. • 563 South Leonard Street, Waterbury, CT 07608 • HubbardHall.com • 800-648-3412

Product Bulletin

Product Name: Metal Guard 850 Product Code: 2508050 Revision Date: May 19, 2020

Operating Conditions

Metal Guard 850 can be applied by immersion or spray. Solutions of Metal Guard 850 are non-foaming. Drying can be accelerated by heating the Metal Guard 850 solution or by drying in a heated atmosphere.

| Concentration | 2 – 4% by volume |
|---------------|------------------------|
| Temperature | Ambient – 160°F (71°C) |

Corrosion Protection Properties

Metal Guard 850 may be classified as a non-severe inhibitor, that is, it should not be used on parts or fabrications that are stored outdoors under exposure to the elements and temperature extremes. Metal Guard 850 solution should be used on parts that are stored indoors or wrapped or boxed after the Metal Guard 850 solution has dried.

Titration Method

- 1. Using a graduated cylinder, measure 25 mL of solution and place in a 250 Erlenmeyer flask.
- 2. Add 5 drops Methyl Orange Indicator.
- 3. Titrate with 0.5 N Hydrochloric Acid to red end point.
- 4. Record mL used.

Calculation

Concentration = mL of 0.5 N HCl x 0.45

Test Kit Method

- 1. Using syringe place 2 mL solution in flask and add 50 mL D.I. water.
- 2. Add 5 drops of Methyl Orange Indicator.
- 3. Add 0.72 N Hydrochloric Acid solution dropwise to red end point.
- 4. Record the number of drops used.

Calculation

Concentration = # Drops of 0.72 N HCl X 0.29

Waste Disposal

Discharge to a disposal system. In order to be completely informed on the latest regulations for your area, please contact the local authorities.









Better chemistry. Better business.

Hubbard-Hall Inc. • 563 South Leonard Street, Waterbury, CT 07608 • HubbardHall.com • 800-648-3412

Product Bulletin

Product Name: Metal Guard 850 Product Code: 2508050 Revision Date: May 19, 2020

WARRANTY: THE QUALITY OF THIS PRODUCT IS GUARANTEED ON SHIPMENT FROM OUR PLANT. IF THE USE RECOMMENDATIONS ARE FOLLOWED, DESIRED RESULTS WILL BE OBTAINED. SINCE THE USE OF OUR PRODUCTS IS BEYOND OUR CONTROL, NO GUARANTEE EXPRESSED OR IMPLIED IS MADE AS TO THE EFFECTS OF SUCH USE, OR THE RESULTS TO BE OBTAINED.

Our people. Your problem solvers.

For more information on this process please call us at 1-800-648-3412

or techservice@hubbardhall.com











